

## SYMMETRY PECULIARITIES OF THE INTRACRYSTALLINE FIELDS LAYERED SEMICONDUCTOR CRYSTALS $(\text{PbI}_2)_{(1-x)} (\text{BiI}_3)_x$

IGOR VERTEGEL, EUGENE CHESNOKOV and ALEKSANDR OVCHARENKO, *Institute of Physics National Academy of Sciences of Ukraine 46, Prospect Nauki, 03680 Kiev, Ukraine.*

In this work the results of the investigation of the  $^{127}\text{I}$  NQR spectra at 77K for mixed layered semiconductor crystals  $(\text{PbI}_2)_{(1-x)} (\text{BiI}_3)_x$  in a wide range of value ( $0 < x < 0.50$ ) are presented. It is shown that in the range  $0.05 < x < 0.20$  of admixture  $\text{PbI}_2$  the observed behavior of parameters of the  $^{127}\text{I}$  NQR spectra testify about entrance of admixture atoms  $\text{PbI}_2$  into the crystal layers. It is shown, that at  $0.05 < x < 0.20$  clusters from groups of atoms  $\text{PbI}_2$  insular type can be formed, which lay within the limits of the layers of crystal  $(\text{PbI}_2)_{(1-x)} (\text{BiI}_3)_x$ . Upon further increasing of the containing of admixture  $\text{PbI}_2$  in crystal  $\text{BiI}_3$  the new  $^{127}\text{I}$  NQR line is appearing. The observed at  $x \sim 0.20$  the new line in spectrum  $^{127}\text{I}$  NQR can testify that the mixed crystal  $(\text{PbI}_2)_{(1-x)} (\text{BiI}_3)_x$  undergoes structural phase transition. It is concluded that at  $x > 0.20$  a new crystal presents a solid mixture glassy crystal of substitution type in which of  $\text{PbI}_2$  atoms are fully or partially are ordering and lay between crystal<sup>a</sup>.

---

<sup>a</sup>A.I.Barabash, I.G.Vertegel, E.D.Chesnokov et.al., Ukr. J.Phys., 2011, vol.56, No.2, p.158-160.